

add serial number

FABRICATION METHOD OF SEMICONDUCTOR INTEGRATED CIRCUIT DEVICE

BACKGROUND OF THE INVENTION

The present invention relates to a fabrication technique ^{for use in the manufacture} of a semiconductor integrated circuit device, and, more particularly, to a technique which is ~~effectively~~ applicable to resin molding in assembly using boards.

In ~~the~~ conventional resin molding, opening degree adjustment means, which adjusts ^{the} ~~an~~ opening degree of each air vent portion, is provided to the air vent portion of a mold, and a driving mechanism, ^{is provided to drive} ~~which drives~~ the opening degree adjustment means ~~is provided~~ (for example, refer to ~~Patent Document 1~~).
Patent Document 1: Japanese Unexamined Patent Publication No. Hei 10(1998)-92853 (Fig. 1)).

To perform transfer molding by mounting semiconductor integrated circuit chips on a multilayered printed wiring circuit board or the like and inserting the multilayered printed wiring circuit board or the like between molds, ^{in contrast to} ~~different from~~ general lead frames having ^a relatively small thickness error or the like, the thickness error is relatively large, and, hence, ^{arise} ~~there arise~~ various drawbacks.

That is, when the thickness is excessively small, a gap is formed between an upper mold and a peripheral portion of the board, and, hence, ^{the} ~~a~~ leaking of sealed resin occurs. Accordingly, to compensate for the small thickness, ^{the} ~~a~~ clamping force is

increased so as to depress the board by approximately 1% of the thickness, thus preventing the leaking of sealed resin. However, in this case, when the thickness is excessively large, ~~the~~ excessive deformation arises in the board.

Further, it may be considered that the occurrence of voids or the like due to clogging of resin in the air vent portion can be suppressed by preliminarily preparing data corresponding to ~~the~~ thickness of a lead frame at the time of performing resin molding (resin filling) and adjusting ~~the~~ opening degree adjustment means in the air vent portion of a sealed mold by inputting such data at the time of ~~sealing~~ ^{resin} sealing. However, in such a resin sealing operation, there arise drawbacks ⁱⁿ that each time the thickness of the lead frame is changed, it is necessary to perform the ~~alternation~~ operation of inputting data, and, at the same time, it is necessary to prepare input data for adjusting the opening degree adjustment means corresponding to the frame thickness.

Further, when the resin sealing operation is performed using a resin-made board which is softer than the lead frame, unevenness is liable to be ~~generated~~ ^{occur} on a surface of the board due to warping of the board or ~~the~~ presence/non-presence of wiring, and, hence, in the above-mentioned resin sealing operation, there arises a drawback ⁱⁿ that the opening degree adjustment of the air vent portion in response to ^a ~~the~~ change ^{in the} of thickness of the board and the shape of the surface of the board is extremely

difficult.

Further, when it is necessary to perform resin molding of a plurality of boards using one mold at a time, the above-mentioned method requires a driving mechanism ^{for the} ~~of~~ open degree adjustment means in the sealing mold for every air vent portion, and hence, the structure of the sealing mold becomes complicated and large-sized.

Accordingly, it is an object of the present invention to provide a ^{method of} ~~a~~ fabrication ~~method~~ of a semiconductor integrated circuit device which can enhance ^{the} ~~a~~ yield rate of products.

^{method of} It is a further object of the present invention to provide a ~~a~~ fabrication ~~method~~ of a semiconductor integrated circuit device which can reduce ^{the} ~~a~~ fabrication cost.

It is a still further object of the present invention to provide a ^{method of} ~~a~~ fabrication ~~method~~ of a semiconductor integrated circuit device which can prevent the occurrence of drawbacks at the time of transporting boards in succeeding steps.

^{method of} It is another object of the present invention to provide a ~~a~~ fabrication ~~method~~ of a semiconductor integrated circuit device which can reduce ^{the} ~~a~~ mold clamping force.

The above-mentioned and other objects and novel features of the present invention will become apparent from the description of this specification and ^{the} ~~a~~ attached drawings.

SUMMARY OF THE INVENTION

To briefly explain the ^Asummary of typical ^{aspects}inventions out of the invention disclosed in the present application, ~~they~~ ^{is} are as follows.

That is, the present invention is characterized by ~~the fact that~~ ^{is performed} performing resin molding by filling sealing resin in the inside of a cavity in a state ~~that~~ ^{in which the} depths of air vents in a mold for resin molding are set to a fixed value.

Further, ^A ~~the~~ summary of ^{various features} ~~another invention~~ of the present ~~invention will be~~ ^{the following} application is described by ~~dividing~~ ^{method of} in paragraphs. ~~That is,~~

1. A ^{es} ~~fabrication method~~ of a semiconductor integrated circuit device comprising ^A the steps of:

(a) preparing a multilayered printed wiring circuit board;

(b) mounting semiconductor chips on the multilayered printed wiring circuit board;

(c) arranging the multilayered printed wiring circuit board over which the semiconductor chips are mounted on a mold surface of a mold for resin molding and, thereafter, closing the mold; and

(d) filling sealing resin in the inside of a cavity formed in the mold such that respective depths of a plurality of air vents formed through the cavity are set to a fixed value by projecting movable pins provided for respective air vents toward the air vent side by pushing using ^{the} ~~a~~ pressure of a spring.

^{method of} 2. A ~~fabrication method~~ of a semiconductor integrated

circuit device comprising ^{es}~~ing~~ the steps of:

(a) preparing a multilayered printed wiring circuit board;

(b) preparing a mold for resin molding which includes a cavity and a plurality of air vents which are formed to ~~be~~ communicated with the cavity, wherein movable pins are provided for respective air vents and a cavity-side depths of the movable pins in the air vents are set ^{to be} greater than the depths of the movable pins at the outside of the movable pins;

(c) mounting semiconductor chips on the multilayered printed wiring circuit board;

(d) arranging the multilayered printed wiring circuit board over which the semiconductor chips are mounted on a mold surface of the mold and, thereafter, closing the mold; and

(e) filling sealing resin in the inside of the cavity such that respective depths of the plural air vents are set to a fixed value using movable pins provided for respective air vents.

~~Further, the summary of another invention of the present application is described below by dividing in paragraphs.~~

^{method of}
3. A ~~fabrication method~~ of a semiconductor integrated circuit device comprising the steps of:

(a) preparing a multilayered printed wiring circuit board;

(b) mounting semiconductor chips on the multilayered

printed wiring circuit board;

(c) arranging the multilayered printed wiring circuit board over which the semiconductor chips are mounted on a mold surface of a mold for resin molding and, thereafter, closing the mold; and

(d) filling sealing resin in the inside of the cavity such that respective depths of the plural air vents which are formed to be communicated with the cavity of the mold are set to a fixed value by projecting movable pins provided for respective air vents.

4. A ^{method of} fabrication ~~method~~ of a semiconductor integrated circuit device according to the above-mentioned ^{paragraph 3} ~~third invention~~, wherein grooves are formed over respective distal ends of the plural movable pins and air inside the cavity is leaked to the outside of the cavity through the grooves formed in the respective movable pins at the time of filling resin in the inside of the cavity.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is an enlarged partial cross-sectional view showing one example of the structure of a mold ^{to be} used in a ^{method of} fabrication ~~method~~ of a semiconductor integrated circuit device according to an embodiment of the present invention ^{as seen} when the mold is in an open state;

Fig. 2 is an enlarged partial cross-sectional view

showing the structure of a cross section taken along a line A-A in Fig. 1;

Fig. 3 is a cross-sectional view of an enlarged portion showing one example of the structure of air vents at the time of filling resin in the inside of the mold shown in Fig. 1;

Fig. 4 is an enlarged partial cross-sectional view showing the structure of a cross section taken along a line B-B in Fig. 3;

Fig. 5 is a partial cross-sectional view showing one example of the movable pin supporting structure of an upper mold of the mold shown in Fig. 1;

Fig. 6 is a plan view showing one example of the cavity-side structure of the upper mold shown in Fig. 5;

Fig. 7 is a partial cross-sectional view showing one example of the structure of a lower mold of the mold shown in Fig. 1;

Fig. 8 is a plan view showing one example of the structure of a mold surface of the lower mold shown in Fig. 7;

Fig. 9 is an enlarged partial cross-sectional view showing the structure of a portion C in Fig. 5;

Fig. 10 is an enlarged partial plan view showing the structure of a portion D in Fig. 5;

Fig. 11 is an enlarged partial cross-sectional view showing the structure of a cross section taken along a line E-E in Fig. 10;

Fig. 12 is a plan view showing one example of the structure of the upper mold of ^athe mold for collective molding used in the ^{method of}~~fabrication method~~ of ^athe semiconductor integrated circuit device ^{according to an}~~of the~~ embodiment 1 of the present invention;

Fig. 13 is a plan view showing one example of the structure of the lower mold which constitutes a ^{pair}~~couple~~ together with the upper mold shown in Fig. 12;

Fig. 14 is a cross-sectional view showing one example of the structure of the semiconductor integrated circuit device which is assembled by the ^{method of}~~fabrication method~~ of ^athe semiconductor integrated circuit device ^{according to}~~of the~~ embodiment 1 of the present invention;

Fig. 15 is a plan view showing one example of the structure of the multi-cavity printed wiring circuit board which is used by the ^{method of}~~fabrication method~~ of ^athe semiconductor integrated circuit device ^{according to}~~of the~~ embodiment 1 of the present invention;

Fig. 16 is an enlarged cross-sectional view showing one example of the relationship between the printed wiring circuit board and guide pins at the time of resin molding in the ^{method of}~~fabrication method~~ of ^athe semiconductor integrated circuit device ^{according to}~~of the~~ embodiment 1 of the present invention;

Fig. 17 is a plan view showing one example of the printed wiring circuit board structure after resin molding in the ^{method of}~~fabrication method~~ of ^athe semiconductor integrated circuit

according to
device ~~of the~~ embodiment 1 of the present invention;

Fig. 18 is a plan view showing one example of a dicing
line for dividing ^{a wafer} into pieces after resin molding in the ^{method of}
fabrication ~~method~~ of the semiconductor integrated circuit
device ~~of the~~ ^{according to} embodiment 1 of the present invention;

Fig. 19 is a plan view showing one example of the
structure of runners and culls after resin molding in the ^{method of}
fabrication ~~method~~ of ^a ~~the~~ semiconductor integrated circuit
device ~~of the~~ ^{according to} embodiment 1 of the present invention;

Fig. 20 is a plan view showing one example of the
structure after dividing ^{a wafer} into pieces in the ^{method of} fabrication ~~method~~
of ^a ~~the~~ semiconductor integrated circuit device ^{according to} ~~of the~~
embodiment 1 of the present invention;

Fig. 21 is a bottom view showing one example of the
structure after dividing ^{a wafer} into pieces in the ^{method of} fabrication ~~method~~
of ^a ~~the~~ semiconductor integrated circuit device ^{according to} ~~of the~~
embodiment 1 of the present invention;

Fig. 22 is a perspective view showing the structure of
a semiconductor integrated circuit device according to a
modification assembled by the ^{method of} fabrication ~~method~~ of ^a ~~the~~
semiconductor integrated circuit device ^{according to} ~~of the~~ embodiment 1 of
the present invention;

Fig. 23 is a side view showing with a part broken away ^{of}
the structure of the semiconductor integrated circuit device
shown in Fig. 22;

Fig. 24 is a plan view showing one example of the structure at the time of completion of resin molding in the manufacture of the semiconductor integrated circuit device shown in Fig. 22;

Fig. 25 is a plan view showing one example of the structure of an upper mold of a mold for simultaneously molding a plurality of semiconductor integrated circuit devices used ~~in a fabrication method~~ ^{the method of} of a semiconductor integrated circuit device according to an embodiment 2 of the present invention;

Fig. 26 is a plan view showing one example of the structure of a lower mold which constitutes a pair with the upper mold shown in Fig. 25;

Fig. 27 is a plan view showing one example of the structure of a printed wiring circuit board after resin molding ~~in the fabrication method~~ ^{method of} of ~~the~~ ^a semiconductor integrated circuit device according to the embodiment 2 of the present invention;

Fig. 28 is a cross-sectional view showing one example of the structure of a semiconductor integrated circuit device assembled by the ~~the fabrication method~~ ^{method of} of ~~the~~ ^a semiconductor integrated circuit device according to the embodiment 2 of the present invention; and

Fig. 29 is a bottom view showing one example of the structure of the semiconductor integrated circuit device shown in Fig. 28.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Embodiments of the present invention ^{will be} ~~are~~ explained in detail in conjunction with ^{the accompanying} ~~attached~~ drawings hereinafter.

Although the explanation ^{will be} ~~is~~ mainly focused on an ^{applied} ~~application~~ example to a sheet mold (an ^{applied} ~~application~~ example to an upper side sheet) hereinafter, the present invention is not limited to such an application. When ^a ~~the~~ sheet is not used, ^{the} ~~it~~ leaking of resin or the like is liable to easily occur, and hence, there exists large possibility that the application of the present invention becomes necessary. Further, when ^a ~~the~~ sheet is used, due to a coupled effect between the present invention and the sheet, it is estimated that the mass productivity and the effect of preventing leaking of resin or the like can be largely enhanced.

In this specification, when "multilayered printed wiring circuit board" is referred to, this implies printed wiring circuit boards in two or more layers. Here, "two layers" means that there are two wiring layers. Further, "wiring" includes a land array, an electrode matrix and the like besides usual printed wiring. Further, when "semiconductor integrated circuit device", "integrated circuit chip", "semiconductor chip", "semiconductor pellet" and the like are referred to in this specification, they include not only those ^{elements which} ~~who~~ are prepared on a silicon wafer, but also those ^{elements} ~~which~~ are prepared on other ^{types of} ~~types of~~

board, such as a TFT liquid crystal substrate or the like, unless otherwise specified accordingly.

Further, in the embodiments described hereinafter, when it is necessary for the sake of convenience, the explanation is made by dividing the invention into a plurality of sections or a plurality of embodiments.. However, unless otherwise specified particularly, these embodiments are not irrelevant to each other and there exists the relationship that one embodiment is a modification, a detailed explanation or a complementary explanation of a portion or the whole of ^{the} other embodiments.

Further, in the embodiments described hereinafter, when ~~the~~ reference is made ~~with respect~~ ^a to the number and the like (including ^a number, numerical values, quantity, range and the like) of elements, unless otherwise specified and unless ~~otherwise~~ ^{it is apparent that} the number and the like of elements are definitely limited to the specific number in principle, the number and the like are not limited to such specific number and may be a number above or below the specific number.

Further, in the embodiment described hereinafter, it is needless to say that ~~the~~ constituent elements (including element steps and the like) are not always indispensable unless otherwise specified or unless they are considered indefinitely indispensable in principle.

In the same manner, in the embodiments described

hereinafter, when ~~the~~ reference is made with respect to the shape, the positional relationship and the like of the constituent elements, unless otherwise specified or unless it is indefinitely considered unreasonable in principle, these shapes and positional relationships substantially include those which approximate or are similar to these shapes. The same goes for the above-mentioned numerical values and ranges.

Further, in all ^{of the} drawings ~~which are served for explaining the embodiments of the present invention, the~~ constitutional elements which have the same functions are given ^{the} same symbols and ~~the~~ repeated explanation thereof is omitted.

(Embodiment 1)

~~Fig. 1 is an enlarged partial cross-sectional view showing one example of the structure of a mold used in a fabrication method of a semiconductor integrated circuit device according to an embodiment of the present invention when the mold is in an open state, Fig. 2 is an enlarged partial cross-sectional view showing the structure of a cross section taken along a line A-A in Fig. 1, Fig. 3 is a cross-sectional view of an enlarged portion showing one example of the structure of air vents at the time of filling resin in the inside of the mold shown in Fig. 1, Fig. 4 is an enlarged partial cross-sectional view showing the structure of a cross section taken along a line B-B in Fig. 3, Fig. 5 is a partial cross-sectional view showing one example of the movable pin supporting structure~~

~~of an upper mold of the mold shown in Fig. 1, Fig. 6 is a plan~~
view showing one example of the cavity-side structure of the
upper mold shown in Fig. 5, Fig. 7 is a partial cross-sectional
view showing one example of the structure of a lower mold of
the mold shown in Fig. 1, Fig. 8 is a plan view showing one example
of the structure of a mold surface of the lower mold shown in
Fig. 7, Fig. 9 is an enlarged partial cross-sectional view
showing the structure of a portion C in Fig. 5, Fig. 10 is an
enlarged partial plan view showing the structure of a portion
D in Fig. 6, Fig. 11 is an enlarged partial cross-sectional view
showing the structure of a cross section taken along a line E-E
in Fig. 10, Fig. 12 is a plan view showing one example of the
structure of the upper mold of the mold for collective molding
used in the fabrication method of the semiconductor integrated
circuit device of the embodiment 1 of the present invention,
Fig. 13 is a plan view showing one example of the structure of
the lower mold which constitutes a couple together with the
upper mold shown in Fig. 12, Fig. 14 is a cross-sectional view
showing one example of the structure of the semiconductor
integrated circuit device which is assembled by the fabrication
method of the semiconductor integrated circuit device of the
embodiment 1 of the present invention, Fig. 15 is a plan view
showing one example of the structure of the multi-cavity printed
wiring circuit board which is used by the fabrication method
~~of the semiconductor integrated circuit device of the~~

~~embodiment 1 of the present invention, Fig. 16 is an enlarged cross-sectional view showing one example of the relationship between the printed wiring circuit board and guide pins at the time of resin molding in the fabrication method of the semiconductor integrated circuit device of the embodiment 1 of the present invention, Fig. 17 is a plan view showing one example of the printed wiring circuit board structure after resin molding in the fabrication method of the semiconductor integrated circuit device of the embodiment 1 of the present invention, Fig. 18 is a plan view showing one example of a dicing line for dividing into pieces after resin molding in the fabrication method of the semiconductor integrated circuit device of the embodiment 1 of the present invention, Fig. 19 is a plan view showing one example of the structure of runners and culls after resin molding in the fabrication method of the semiconductor integrated circuit device of the embodiment 1 of the present invention, Fig. 20 is a plan view showing one example of the structure after dividing into pieces in the fabrication method of the semiconductor integrated circuit device of the embodiment 1 of the present invention, Fig. 21 is a bottom view showing one example of the structure after dividing into pieces in the fabrication method of the semiconductor integrated circuit device of the embodiment 1 of the present invention, Fig. 22 is a perspective view showing the structure of a semiconductor integrated circuit device according to a~~

~~modification assembled by the fabrication method of the~~
semiconductor integrated circuit device of the embodiment 1 of
the present invention, Fig. 23 is a side view showing with a
part broken away the structure of the semiconductor integrated
circuit device shown in Fig. 22, and Fig. 24 is a plan view
showing one example of the structure at the time of completion
of resin molding in the manufacture of the semiconductor
integrated circuit device shown in Fig. 22.

is directed to a method of
This embodiment 1 ~~explains the~~ fabrication method of a
semiconductor integrated circuit device in which the
semiconductor integrated circuit device is assembled such that
a printed wiring circuit board is used and a sealing body 44
(see Fig. 14) is formed over the board by performing resin
molding on the board.

The explanation of
In this embodiment 1, ~~the explanation is made by taking~~
a CSP (Chip Size Package) 43, which is assembled using a
multi-cavity printed wiring circuit board (board) ²⁰40, shown in
Fig. 15, is taken as an example of the semiconductor integrated circuit
device.

The CSP 43 shown in Fig. 14 is a thin semiconductor
package of a chip laminated type. With respect to ~~To explain~~ the structure of
the CSP 43, the CSP 43 is constituted of a printed wiring circuit
board (board) 41, which has a main surface 41a and a back surface
41b, wherein a chip mounting region 40b and leads 41c, which
constitute a plurality of lines shown in Fig. 15, are formed over

the main surface 41a. ^{Two} semiconductor chips 4 ~~which~~ are mounted on the chip mounting region 40b of the main surface 41a of the printed wiring circuit board 41 by lamination, ^{and} a plurality of wires 5 ~~which~~ respectively connect bonding electrodes 4b of respective semiconductor chips 4 and the leads 41c which correspond to the bonding electrodes 4b. ^{The} sealing body 44 ~~which~~ seals the semiconductor chips 4 and the plural wires 5 with resin, and solder balls 42 ~~which~~ are mounted on the back surface 41b of the printed wiring circuit board 41 and constitute a plurality of external terminals.

Here, the CSP 43 is formed by using a multi-cavity printed wiring circuit board 40 over which a plurality of device regions (device forming regions) 40c, respectively having chip mounting regions 40b, are formed over a main surface 40a in a matrix array. In a resin sealing (resin molding) step after wire bonding, the plural device regions 40c, which are arranged in ^a ~~the~~ matrix array, are covered with one cavity of a mold 6 and resin sealing is collectively formed (hereinafter, such resin sealing method is referred to as collective molding); and, thereafter, the resin sealed structure is divided into pieces by dicing so as to form the CSP 43.

Here, the printed wiring circuit board 41 is a thin board which is constituted by forming wiring made of copper or the like over a resin board made of glass-epoxy-based resin or the like.

~~no 18~~ Further, the sealing body 44 is made of epoxy resin, for example, and is formed by resin molding.

Further, the wires 5 are formed of a gold line, for example.

Next, the structure of an upper mold 7, ~~is explained~~ which constitutes a first mold, and a lower mold 8, which constitutes a second mold, ~~shown in Fig. 1,~~ ^{will be explained with reference to molds} which are used in the resin sealing step of the ~~method~~ ^{method of} fabrication of the semiconductor integrated circuit device of this embodiment 1. Here, with respect to the first mold and the second mold, the second mold may be constituted by the upper mold 7 and the first mold may be constituted by the lower mold 8.

First of all, as shown in Fig. 1 and Fig. 5, the upper mold 7 is mainly constituted of cull blocks 7a and a cavity block 7b, wherein one collective cavity 7h, which is capable of covering the main surface 40a of the multi-cavity printed wiring circuit board 40 at the time of performing resin sealing, is formed in the cavity block 7b.

Further, around the collective cavity 7h, as shown in Fig. 6, a plurality of air vents 7c, a plurality of culls 7d and a plurality of gates 7i are formed. Among these elements, the plural gates 7i and the plural air vents 7c are formed in parallel respectively along two opposing longitudinal sides of the rectangular collective cavity 7h such that they face each other, while the culls 7d are formed in a plural number in the

vicinity of the gates 7i.

Further, in the upper mold 7, ^{there are} a plurality of movable pins 1, which are formed such that the movable pins 1 project into respective air vents 7c, and return pins 7f, which separate the upper mold 7 from the lower mold 8 at the time of releasing the mold 6 after ^{resin} filling ~~resin are arranged~~. As shown in Fig. 1, respective movable pins 1 are connected to movable pin driving springs 2 such that the movable pins 1 are capable of applying a load of approximately 9.8 Newton to 49 Newton (1-5 kg) to the multi-cavity board 40 and are formed such that the movable pins 1 project respectively into the air vents 7c.

The mold according to this embodiment 1 includes the plural air vents 7c, and ^{it} is capable of performing resin molding by filling sealing resin 9, as shown in Fig. 3, ^{while} setting ^{the} depths of respective air vents 7c to a fixed value irrespective of ^{the} board thickness and ^{the} state of ^{the} board surface, such as an unevenness at the time of resin molding.

Accordingly, the movable pins 1 which have ^{the} distal ends thereof respectively projected into the air vents 7c corresponding to respective air vents 7c are formed, and grooves 1a which constitute air passages, as shown in Fig. 11, are formed in distal ends of respective movable pins 1.

Further, the movable pins 1 are connected with the movable pin driving springs 2 in the inside of the upper mold 7 such that the load, which is far ^{smaller} ~~small~~, compared with ^{the} ~~a~~ clamping

force of the mold 6 and is set at a level which does not deform or damage the board, is applied to the multi-cavity printed wiring circuit board 40 at the time of clamping the mold, as shown in Fig. 3. Here, the clamping force of the mold 6 is, for example, 150,000 Newton or approximately 15,000 kg-weight per one board in a display unit of a general-purpose device, wherein a portion of the board where the clamping force acts is an annular region having a width of approximately 1 mm around an outer portion of ~~a~~^{the} mold cavity. Taking a rectangular collective mold board having a size of 151 mm × 66 mm as an example, the annular region has a size of 148 mm × 60 mm, a width of 0.8 mm and an area of 352 mm². Further, the load which is far ~~smaller~~^{smaller} compared with the clamping force of the mold frame 6 and does not deform or damage the board is, for example, 9.8 Newton to 49 Newton and is approximately 1-5 kg-weight in a display of a general-purpose device (indicating a value per one movable pin). Taking the movable pin 1 having a diameter of 6 mm^{as an example}, a portion over which this force acts is a cylindrical cross-sectional area which is approximately 28 mm².

This is because, in the structure of the mold 6 according to the embodiment 1, the resin injection pressure is not directly applied to the respective air vents 7c, and, hence, as the spring force applied to the movable pins 1, the load at a level which allows the movable pins 1 to slightly push the board is sufficient. Accordingly, only the load of approximately 9.8

Newton to 49 Newton (1-5 kg) is applied to the movable pins 1 using the movable pin driving springs 2.

Further, the movable pins 1 are formed such that ^{the} ~~a movable~~ ^{of movement} amount thereof in the vertical direction (N indicated in Fig. 3 and Fig. 9) becomes 100- 200 μm , for example.

Due to such a constitution, even when there exists irregularities with respect to the thickness of the board or an unevenness is formed attributed to wiring or the like on the surface of the board depending on the positions of the board, at the time of clamping the molds, the distal ends of respective movable pins 1 which project into the air vents 7c at respective board positions automatically correspond to the board condition at respective board positions so that the distal ends of respective movable pins 1 are brought into close contact with the board.

Here, even when the stop positions of respective movable pins 1 in the vertical direction differ depending on the irregularities of the thickness of the board and the condition of the board surface, such as an unevenness, provided that the depths of the grooves 1a formed in the distal ends of respective movable pins 1 are set to a fixed value, it is possible to set the depths for respective air vents 7c to a fixed value, and hence, the sealing resin 9 can be filled by automatically setting the depths of respective air vents 7c to a fixed value.

Here, the depths of the air vents 7c ^{will be further} ~~are~~ explained.

The air vent 7c can be classified into four portions consisting of a movable-pin front portion, a movable-pin portion (or an air vent main portion), a movable-pin rear portion and a release portion, which ^{portions} are arranged ^{in sequence} in the direction from the cavity (collective cavity 7h) to a flow passage. To explain the movable-pin front portion, assuming that the tolerance of ^{the} thickness of the resin board is approximately $\pm 30 \mu\text{m}$, for example, even when the board has the largest thickness, by setting the depth of the air vent 7c to approximately 60 to 70 μm , ^{an} the effective air vent depth of approximately 30 to 40 μm can be ensured. ⁱⁿ this case, when the film 3 which constitutes the sheet is applied, the depth is not measured from the upper mold surface, but is measured from the lower surface of the sheet, as shown in Fig. 9. When there is no sheet, it is needless to say that the depth is measured from the surface of the upper mold. Accordingly, assuming ^{that} the usual thickness of the sheet ^{is} as 50 μm , it is estimated that the actual thickness of the sheet becomes approximately 30 μm as a result of elongation at the time of molding the sheet, and hence, the depth of mechanical cuts for the air vents becomes the above-mentioned value + the actual thickness of the sheet in performing the sheet molding. By setting the depth of cuts to approximately 40 to 50 μm at the movable pin portion, the value can be automatically ensured. It is sufficient to set the depth of the cuts to approximately 50 to 60 μm at the movable-pin rear

portion. This is because the movable-pin rear portion is immediately connected with the releasing portion having a depth of approximately $150\mu\text{m}$.

By setting the effective depth of the main portion of the air vents 7c to a fixed value irrespective of the thickness of the printed wiring circuit board or the like (including the lead frame) in the above-mentioned manner, it is possible to effectively prevent leaking of resin without excessively increasing the clamping force (for example, in the above-mentioned example, ~~the~~^a clamping force having up to 5000 kg-weight per one board can excessively deform the board).

Further, when the tolerance of the thickness of the board is slightly set in the minus direction, ^aleaking of ~~the~~ resin is liable to easily occur. In the mold 6 according to the embodiment 1, since the movable pin 1 projects ^{beyond} ~~exceeding~~ the mold surface 7g, the movable pin functions as a plug and leaking of the sealing resin 9 (leaking of resin) is prevented.

In the mold 6 according to the embodiment 1, as shown in Fig. 1, the depth differs between the depth (L) of the cavity side (movable pin front portion) of the movable pin 1 in the air vent 7c and the depth (M) of the outside (movable-pin rear portion) of the movable pin 1, wherein the depth (L) of the cavity side of the movable pin 1 is set ^{to be} greater than the depth (M) of the outside of the movable pin 1. For example, it is preferable to set the depth L to approximately 60 to $70\mu\text{m}$ and the depth

M to approximately 50 to 60 μ m.

Due to such a constitution, even when ^a~~the~~ deformation, such as a warp, occurs in the vicinity of a path leading from the gate 7i to the cavity on the board, there is no possibility that the air vent 7c in the vicinity of the gate 7i ^{will be} ~~is~~ clogged by the board, and, hence, the air vent 7c in the vicinity of the gate 7i can be reliably ensured.

Next, the width of the air vent 7c ^{will be} ~~is~~ explained.

In the mold 6 according to this embodiment 1, as shown in Fig. 10, ^{the} ~~a~~ vent width (P) of the air vent 7c at the cavity side of the movable pin 1 is set ^{to be} ~~is~~ smaller than ^{the} ~~a~~ pin diameter (Q) of the movable pin 1.

^{to be} In other words, the pin diameter (Q) of the movable pin 1 is set ~~is~~ larger than the vent width (P) of the air vent 7c at the cavity side of the movable pin 1.

For example, assuming ^{that} ~~the~~ the pin diameter (Q) of the movable pin 1 ^{is} ~~as~~ 5mm, it is preferable to set the vent width (P) of the air vent 7c at the cavity side to approximately 4mm and ^{the} ~~a~~ vent width (S) of the air vent 7c at the outside of the movable pin 1 to approximately 5mm, and ^{the} ~~a~~ width (R) of the groove 1a of a distal end of the movable pin 1 to 2 to 3mm.

Accordingly, the movable pins 1 function as ~~the~~ plugs and stop ^{any} ~~a~~ leaking of resin which occurs when the tolerance of the thickness of the board is slightly set in the minus direction, and, hence, leaking of the sealing resin 9 (leaking of resin)

can be surely prevented.

In the mold 6 of this embodiment 1, movable-pin rammers (pusher rods) ²⁰⁰ 7j, shown in Fig. 9, which makes the movable pins 1 project to the air vent side when the mold 6 is released, are formed over the upper mold 7.

Due to such a constitution, when the mold 6 is released, it is possible to further push the movable pins 1 so as to make the movable pins 1 project into the air vent side with the use of the movable-pin rammers 7j.

The movable-pin rammers 7j are configured such that the movable-pin rammers 7j are held by a rammer holder 7l, and the rammer holder 7l is capable of pushing the movable-pin rammers 7j ^{in response to the} ^a ~~with a~~ spring force of ^a movable-pin pushup spring 7k.

Due to such a constitution, by pushing out the movable pins 1 to the air vent side with the use of the movable-pin rammers 7j at the time of releasing the mold 6, even when the sealing resin 9 intrudes ^{at} the peripheries of the movable pins 1, it is possible to prevent the operation of the movable pins 1 from being worsened, and, hence, it is possible to ensure ^a ~~the~~ sufficient maintenance of the operation of the movable pins 1.

Further, in the mold 6 according to the embodiment 1, the resin molding is performed over the board, and, hence, a plurality of suction holes 7m, 8f are formed in the upper mold ^{, respectively,} 7 and the lower mold 8, such that upper and lower films 3 (sheets) are sucked and brought into close contact with the mold surfaces

7g, 8h at the time of performing resin molding. These films 3 are ~~served~~ ^{used} for preventing the adhesion of resin to the wiring over the board and damage ~~on~~ ^{to} the wiring at the time of clamping the molds. By arranging the films 3 respectively on the mold surface 7g of the upper mold 7 and the mold surface 8h of the lower mold 8 at the time of resin molding, by ~~sucking~~ ^{suction applied to} the respective films 3 through the suction holes 7m, 8f and by heating the mold 6 at a given temperature (for example, approximately 180°C), the films 3 are brought into close contact with the respective mold surfaces 7g, 8h and, thereafter, the resin is filled.

Here, as shown in Fig. 1, the suction holes 7m are formed in the upper frame 7 in the vicinity of the movable pins 1. By ~~sucking~~ ^{applying suction to} the film 3 through the suction holes 7m before clamping the mold and also by heating the mold 6 to a given temperature so as to bring the film 3 into close contact with the mold surface 7g, as shown in Fig. 2, it is possible to bring the film 3 into contact with the grooves 1a formed in the distal ends of the movable pins 1, such that the film 3 follows the contour of the grooves 1a.

Accordingly, even when the film 3 is arranged on the mold surface 7g, it is possible to form the grooves 1a in the distal ends of the movable pins 1 at the time of clamping the molds, as shown in Fig. 4.

Here, the films 3 which are used for resin molding are,

for example, formed of a thin film, such as a fluorine-based film material which has a thickness of approximately 50 μ m and is extremely flexible.

On the other hand, the lower mold 8 of the mold 6 is, as shown in Fig. 7, mainly constituted of pot holders 8b and a cavity block 8c, wherein a plurality of pots 8d are formed in the pot holder 8b corresponding to the plural culls 7d formed in the upper mold 7. Plungers ³⁰⁰8g, shown in Fig. 16, which push out the sealing resin 9, are arranged in the respective pots 8d.

Further, in the cavity block 8c of the lower mold 8, a lower-mold cavity 8e is formed, as shown in Fig. 8, while guide pins 8a, which guide the board, such as the multi-cavity board 40 arranged on the mold surface 8h, are mounted on the cavity block 8c.

Here, Fig. 12 shows ^{an}the upper mold 7 which is capable of resin-molding two sheets of multi-cavity boards 40 at ^{one}a time, wherein collective cavities 7h for arranging two sheets of multi-cavity boards 40 are respectively formed at both sides of a collective sealing cull 7d, while a plurality of air vents 7c are formed in parallel at sides of the collective cavities 7h opposite to the ^{cull}~~cav~~ 7d. Each air vent 7c has ^athe structure which allows the air vent 7c ^{to}communicate with the collective cavity 7h so as to release air at the time of ^{resin}filling ~~resin~~. Further, in each air vent 7c, the movable pin 1 is arranged in a projected manner.

Further, Fig. 13 shows the structure of the lower mold 8 which forms a pair with the upper mold 7 shown in Fig. 12.

Next, the ^{method of} fabrication ~~method~~ of the semiconductor integrated circuit device (CSP 43) of the embodiment 1 ^{will be} ~~is~~ explained.

First of all, the multi-cavity board 40 shown in Fig. ^{is prepared} 15 ^{are formed in a matrix array,} over which a plurality of device areas 40c, each of which has ^a ~~the~~ chip mounting area 40b including ^a ~~the~~ chip mounting portion and a plurality of leads 41c (see Fig. 14) ~~are formed in a matrix array is prepared.~~

Thereafter, on the chip mounting areas 40b of the device areas 40c of the main surface 40a of the multi-cavity board 40, semiconductor chips 4 are mounted by means of an adhesive or the like. Since the CSP 43 of the embodiment 1 is of a chip stacking type, here, firstly, the semiconductor chips 4 at the lower stage are mounted on the chip mounting areas 40b of the respective device areas 40c, and, subsequently, the semiconductor chips 4 at the upper stage are mounted on the semiconductor chips 4 ^{at} ~~at~~ the lower stage.

After the mounting of the chips by stacking is completed, wire bonding is performed.

That is, the bonding electrodes 4b of the semiconductor chips 4 at the lower stage and the lead 41c corresponding to the bonding electrodes 4b are connected to each other by the wires 5, while the bonding electrode 4b of the semiconductor

chip 4 at the upper stage and the lead 41c corresponding to the bonding electrode 4b are connected by the wires 5.

Thereafter, resin molding is performed.

First of all, the upper mold 7 and the lower mold 8 are, for example, heated to a temperature of 180 degree; and, at the same time, as shown in Fig. 1, in the upper mold 7 and the lower mold 8, respectively, by ~~sucking~~ ^{applying suction to} the respective upper and lower films 3 through the suction holes 7m, 8f, the respective films 3 are brought into close contact with the respective mold surfaces 7g, 8h.

Here, at the upper mold 7 side, the movable pins 1 are arranged in the respective air vents 7c in a state ^{such} that the distal ends of movable pins 1 are projected. ^{suction is applied to} When the film 3 ~~is sucked~~ through the sucking hole 7m, the film 3 follows the shape of the mold surface 7g as shown in Fig. 1 and is brought into close contact with the mold surface 7g. At the same time, the film also follows the shape of a groove 1a formed in the distal end of the movable pin 1 and is brought into close contact with the groove 1a as shown in Fig. 2. →

On the other hand, ~~also~~ ^{as well} at the lower mold 8 side, the film 3 is brought into close contact with the mold surface 8h.

Under such a situation, the semiconductor chips 4 are mounted on the mold surface 8h of the lower mold 8, and, at the same time, the multi-cavity board 40 over which the wire bonding is already completed is arranged on the mold surface 8h of the

lower mold 8. Here, the multi-cavity board 40 is positioned by the guide pins 8a, as shown in Fig. 16.

Further, a plurality of device areas 40c of the multi-cavity board 40 are collectively covered with one collective cavity 7h of the upper mold 7 and, thereafter, the upper mold 7 and the lower mold 8 of the mold 6 are clamped together by closing them, as shown in Fig. 3.

Here, since the movable pins 1 are projected in the respective air vents 7c, slightly before the upper mold 7 and the lower mold 8 are completely closed, the distal ends of the movable pins 1 are brought into contact with the main surface 40a of the multi-cavity board 40. Further, immediately after such a contact, the upper mold 7 and the lower mold 8 are closed. Thereafter, since a spring force is always applied to the movable pins 1 by the movable-pin driving springs 2, even after clamping the upper mold 7 and the lower mold 8 together, each movable pin 1 pushes ^{against} the multi-cavity board 40 toward the lower mold 8 side.

That is, since the spring force of the movable pin driving springs 2 is ^{relatively} ~~very~~ small (for example, from 9.8 Newton to 49 Newton: 1 - 5 kg) compared with the mold clamping force (for example, 150,000 Newton: 15,000 kg), even after clamping the molds together, each movable pin 1 pushes ^{against} the multi-cavity board 40 ^{in the direction of} ~~to~~ the mold surface 8h of the lower mold 8 in each air vent 7c. Here, since the load applied by pushing is extremely small, it

is possible to prevent the multi-cavity board 40 from being deformed or damaged.

Due to such a constitution, an air passage in each air vent 7c is attributed to the depth and the width of the groove 1a formed in the distal end of the movable pin 1. Since the grooves 1a formed in the respective movable pins 1 have the same depth and the same width in respective air vents 7c, irrespective of irregularities ⁱⁿ ~~of~~ the thickness of the board or the surface condition of the board, such as unevenness in respective air vents 7c, it is possible to form the air vent structure shown in Fig. 4. As a result, the depths of respective air vents 7c can be set to a fixed value.

Thereafter, in a state ^{in which} ~~that~~ the depths of respective air vents 7c are set to a fixed value, as shown in Fig. 16, the sealing resin 9 is pushed out by the plunger 8g so that the sealing resin 9 is filled in the collective cavity 7h, as shown in Fig. 3.

At the time of filling the resin, even when the multi-cavity board 40 is formed with a slightly larger thickness due to irregularities in thickness, the respective air vents 7c have a fixed depth due to the grooves 1a formed in the distal ends of respective movable pins 1 (the digging depths of the movable pin portions eventually determining the depths of the air vent movable pin portions; in sheet molding, a value obtained by subtracting an actual thickness from the digging depths of the movable pin portions determining the depths of

the air vent movable pin portions), and, hence, it is possible to ensure leakage of the air from the collective cavity 7h, whereby the occurrence of a state ~~that~~ ^{in which} the sealing resin 9 is not sufficiently filled (a resin unfilled state) can be prevented.

Further, even ^{when} the multi-cavity board 40 is formed with a slightly smaller thickness due to ~~the~~ irregularities in thickness, the respective air vents 7c have a fixed depth due to the grooves 1a formed in the distal ends of respective movable pins 1 in the same manner, and, hence, the occurrence of ^{any} ~~the~~ leaking of resin and the occurrence of ^a ~~a~~ welding defect, which is a defect attributed to voids in a surface of the sealing body, can be obviated.

Accordingly, the occurrence of defects can be reduced, and, hence, ^{the} ~~a~~ yield rate of the products can be enhanced.

Especially, when the multi-cavity board 40 is a board which is formed of resin, unevenness attributed to warping of the board or the presence or non-presence of wiring is liable to easily occur. In the mold 6 according to the embodiment 1, the depths of respective air vents 7c can be set to a fixed value irrespective of the conditions of the surface of the board.

Further, the occurrence of the defects can be reduced and the yield rate can be enhanced in the above-mentioned manner, so that, in an appearance inspection carried out after completion of the resin sealing operation, the inspection flow becomes smooth, and, hence, the throughput of the appearance inspection can be

enhanced.

Further, the occurrence of ^{any} leaking of ^{the} resin can be prevented in the air vents 7c, and, hence, the occurrence of adhesion of resin to the main surface 40a of the multi-cavity board 40 outside an allowable range can be prevented.

Accordingly, in the succeeding process after completion of resin sealing, for example, when the multi-cavity board 40 is arranged at a chute of a dicer (a board transfer jig), it is possible to prevent the occurrence of drawbacks, for example, ^{where} ~~that~~ the board cannot be placed in the chute because resin, which adheres to an outer peripheral portion or the like of the board ^{due to} ~~the~~ ^{by} leaking of ^{the} resin, is caught.

Further, the mold 6 according to this embodiment 1 adopts the structure in which the depths of respective air vents 7c are automatically set to a fixed value due to the movable pins 1 mounted on the upper mold 7 at the time of clamping the molds, as a mold clamping force, it is sufficient to set a load which is slightly larger than ^{the} ~~a~~ resin injection pressure irrespective of the structure of the lower mold 8. As a result, the mold clamping force can be reduced compared with ^{the} ~~a~~ mold clamping force for the conventional mold.

Since the mold clamping force can be reduced in this manner, a load applied to the board at the time of clamping the mold can be reduced, whereby the occurrence of drawbacks, such as the formation of cracks in the board or the deformation of

the board can be prevented.

Further, since this embodiment adopts ^athe mold structure in which the depths of respective air vents 7c can be set to a fixed value due to the movable pins 1 which are mounted on the upper mold 7 irrespective of the thickness of the board, ~~an~~ allowable range (tolerance) of the thickness of the board, such as the multi-cavity board 40 or the like, can be broadened.

Accordingly, the fabrication cost of the board can be reduced, and, hence, the fabrication cost of the semiconductor integrated circuit device, such as CSP 43 or the like, can be reduced.

When the resin sealing is finished and the mold 6 is opened, the multi-cavity board 40 which is sealed by resin is taken out from the mold 6.

Here, on the main surface 40a of the multi-cavity board 40, as shown in Fig. 19, the collective sealing portion 45, which is formed by the collective molding, is formed, and, at the same time, runner resins 47, cull resin 48, gate resin 49 and the like are formed.

Thereafter, the runner resin 47, the cull resin 48, the gate resin 49 and the like are removed from the collective sealing portion 45 to obtain a state as shown in Fig. 17.

Ⓐ Further, the multi-cavity board 40 is cut into individual pieces per each device area 40c.

Here, the dicing is performed along dicing lines 46 shown

in Fig. 18, and the multi-cavity board 40 is cut off together with the collective sealing portion 45; and, thereafter, the multi-cavity board 40 is divided into single pieces, as shown in Fig. 20.

Thereafter, as shown in Fig. 21, the assembling of the CSP 43 is completed by mounting a plurality of solder balls 42 on the back surface 41b of the printed wiring circuit board 41, which ~~is~~^{was} formed by the division of the multi-cavity board into single pieces.

Here, the fixing of the solder balls ~~is~~^{on the} 42 may be performed ~~in a state of~~ multi-cavity board 40 before the multi-cavity board 40 is divided into the single pieces by dicing.

In assembling the CSP 43 as explained above, at the time of performing the resin sealing, the film 3 (sheet) is arranged in the mold and, thereafter, the resin is filled. Therefore, the mold surface 7g of the upper mold 7 is covered with the film 3 at the time of filling the resin; and, hence, there is no possibility that the sealing resin 9 intrudes into the movable pin arranging portions connected to the air vents 7c.

Accordingly, there is no possibility that the sealing resin ~~9 is~~^{will become} clogged in the above-mentioned movable pin arranging portions, and, hence, it is possible to ensure the reliable operation of the movable pins 1.

It must be noted, however, that the mold 6 according to the embodiment 1 can be used even when the resin sealing is

performed without using the film 3, such as ~~the~~ resin sealing using ^a~~the~~ board such as a lead frame. In this case, there may be a possibility that the sealing resin 9 intrudes in the above-mentioned movable pin arranging portions and the movable pins 1 are not moved due to clogged resin. However, in the mold 6 according to this embodiment 1, it is possible to forcibly push out the movable pin 1 toward the air vent side ^{means of} by the movable-pin rammer 7j at the time of opening the mold 6.

Accordingly, even when the sealing resin 9 intrudes into the periphery of the movable pin 1, the smooth operation of the movable pin 1 is maintained, and, at the same time, the maintenance of the operation of the movable pin 1 can be performed.

Further, as the mold clamping force, it is sufficient to set a load slightly larger than the resin injection pressure irrespective of the structure of the lower mold 8. As a result, the mold clamping force can be reduced compared with the ~~the~~ mold clamping force ^{used} for the conventional mold.

Since the mold clamping force can be reduced in this manner, ^{the} ~~a~~ load applied to the board at the time of clamping the mold can be reduced, ^{and} the occurrence of drawbacks, such as the formation of cracks in the board or the deformation of the board, can be obviated.

Further, the mold 6 according to the embodiment 1 adopts ^a ~~the~~ structure in which the depths of ^{the} ~~a~~ respective air vents 7c

are automatically set to a fixed value at the time of clamping ^{the} molds using the movable pins 1 mounted on the upper mold 7, and, hence, cumbersomeness, such as the preparation of input data for adjusting the opening degree adjustment means in response to the frame thickness in advance, can be ^{avoided} ~~omitted~~ and, hence, the resin sealing operation can be simplified.

Further, the mold 6 according to the embodiment 1 adopts ^a ~~the~~ structure in which the depths of respective air vents 7c are automatically set to a fixed value at the time of clamping ^{the} molds due to the movable pins 1 mounted on the upper mold 7, and, hence, it is not necessary to provide a large-sized mechanism, such as a driving mechanism for opening degree adjustment means, whereby the constitution of the mold 6 can be simplified.

Accordingly, the mold 6 can be miniaturized and the cost of the mold 6 can be reduced.

Next, a modification of the embodiment 1 ^{will be} ~~is~~ explained.

Fig. 22 shows a CSP 50, which uses a multi-layered printed wiring circuit board 51 as a board, and a portion of the inner structure of the CSP 50 is shown in Fig. 23.

The multi-layered printed wiring circuit board 51 is formed by laminating a plurality of core members 51c made of resin or the like ~~together and~~ ^{the} ~~In an~~ example shown in Fig. 23, two core members 51c are laminated to each other. ^{respectively} A copper pattern 51d is provided to ^{each of the} ~~respective~~ three layers consisting of a main surface 51a, a back surface 51b and the inside of the

board.

Here, the copper patterns 51d formed on the main surface 51a and the back surface 51b are respectively connected by through-hole wiring 51f or the like. Further, the copper patterns 51d formed on the main surface 51a and the back surface 51b are respectively covered with and insulated by a resist film 51e (insulation film), except for the connection portions, respectively.

In the CSP 50 shown in Fig. 23, a semiconductor chip 4 is mounted on the main surface 51a of the multi-layered printed wiring circuit board 51 by way of a die bonding member 10, while the bonding electrode 4b formed on the main surface 4a of the semiconductor chip 4 and the copper pattern 51d formed on the multi-layered printed wiring circuit board 51 are electrically connected by wires 5, and a plurality of solder ball 53, ^{sum} as outer terminals, are mounted on the copper pattern 51d of the back surface 51b.

Further, the semiconductor chip 4 and ^{the} a plurality of wires 5 are sealed with resin ^{to form} using a sealing body 52.

~~Further,~~ Fig. 24 shows ^{the} a state of a multi-cavity board 54 after collective molding in the assembly of the CSP 50, and, collective sealing portion 55, air vent resin 56 and gate resin 57 are formed over the multi-cavity board 54.

Accordingly, the CSP 50 is formed such that, in the resin sealing step of the assembling operation, the collective

sealing portion 55 is formed by sealing the multi-cavity board 54 having the multi-layered printed wiring structure shown in Fig. 24 with resin by collective molding, and, thereafter, the multi-cavity board 54 is divided into single pieces by dicing.

The CSP 50^{also} can be ~~also~~ assembled by the above-mentioned^{method 1} fabrication ~~method~~ of the semiconductor integrated circuit device of the embodiment 1. When the multi-cavity board 54 having the multi-layered printed wiring structure is used, the irregularities in thickness thereof ^{are} is large compared with the irregularities in thickness of ^a the board having ^a the single layer structure. Accordingly, the ^{method 1} fabrication ~~method~~ of the semiconductor integrated circuit device of this embodiment 1, in which ~~the~~ resin sealing can be performed by setting the depths of the air vents 7c to a fixed value irrespective of the thickness of the board, is extremely effective, and, at the same time, the cost of the multi-cavity board 54 can be reduced by alleviating the tolerance of the thickness of the multi-cavity board 54.

Further, although the CSP 43 shown in Fig. 14 or the CSP 50 shown in Fig. 22 are assembled by collective molding using the mold ~~for the collective mold~~ shown in Fig. 12 and Fig. 13, with respect to the ^{method 1} fabrication ~~method~~ of the semiconductor integrated circuit device of this embodiment 1, it is not necessary to form a new mold 6 even when the thickness of the board is changed, when the product type is changed, and, hence, the mold 6 can be used in common.

Accordingly, the fabrication cost can be reduced.

(Embodiment 2)

Fig. 25 is a plan view showing one example of the structure of an upper mold of a mold for simultaneously molding a plurality of semiconductor integrated circuit devices ^{for use} ~~used~~ in a ^{method of} ~~fabrication method~~ of a semiconductor integrated circuit device according to an embodiment 2 of the present invention; Fig. 26 is a plan view showing one example of the structure of a lower mold which constitutes a pair with the upper mold shown in Fig. 25; Fig. 27 is a plan view showing one example of the structure of the board after resin molding in the fabrication ~~method~~ of the semiconductor integrated circuit device according to the embodiment 2 of the present invention; Fig. 28 is a cross-sectional view showing one example of the structure of a semiconductor integrated circuit device assembled by the ^{method of} ~~fabrication method~~ of the semiconductor integrated circuit device according to the embodiment 2 of the present invention; and Fig. 29 is a bottom view showing one example of the structure of the semiconductor integrated circuit device shown in Fig. 28.

The embodiment 2 relates to a ^{method of} ~~fabrication method~~ of the ^{an} ~~the~~ semiconductor integrated circuit device which is assembled by using a multi-cavity board 60, wherein a plurality of the boards are arranged on one mold and these plurality of boards are sealed by resin at ^{one} ~~a~~ time.

Here, Fig. 25 shows an upper mold 7 of the mold for simultaneously molding a plurality of boards. In this embodiment 2, four multi-cavity boards 60 can be sealed by resin at ^{one} ~~a~~ time.

With respect to the upper mold 7 shown in Fig. 25, in individual cavities 7n which are connected to each other by way of culls 7d and runners 7e, air vents 7c are formed, respectively, at a side opposite to the runners 7e. In the same manner as the mold 6 according to the embodiment 1, movable pins 1 are mounted in respective air vents 7c. Also with respect to the mold 6 according to the embodiment 2, the movable pins 1 perform ^a ~~the~~ similar movement as that of the movable pins 1 of the mold 6 according to the embodiment 1.

On the other hand, Fig. 26 shows, with respect to the lower mold 8, which forms a pair with the upper mold 7 shown in Fig. 25, a state of the lower mold 8 after arranging a plurality of multi-cavity boards 60 ^{therein} ~~and~~ performing resin sealing.

The multi-cavity board 60 shown in Fig. 26 is used for assembling of a card-type package (semiconductor integrated circuit device) ^{as} 59 ~~shown~~ in Fig. 28. The card-type package 59 has ^a ~~the~~ structure in which two semiconductor chips 4 are stacked over a main surface 58a of a board for cards 58, and the card-type package 59 has a plurality of semiconductor chips 4 over which other semiconductor chips 4 are mounted close to two semiconductor chips 4, wherein any semiconductor chips 4 are

connected to the board for card 58 by wire bonding.

Further, the plural semiconductor chips 4 and wires 5 are sealed by resin by a sealing body 61, and a plurality of terminals for external connections 64 are formed over a back surface 58b of the board for card 58, as shown in Fig. 29.

Further, Fig. 27 shows a state of the multi-cavity board 60 after performing ~~the~~ resin molding in ^{the} assembling of the card type package 59, wherein a sealing portion 61, air vent resin 62 and gate resin 63 of respective packages are formed over the main surface 60a of the multi-cavity board 60.

Here, also with respect to the assembling of the card type package 59 of the embodiment 2, the resin sealing can be performed in ~~the~~ ^{the} substantially same manner as the resin sealing method of the embodiment 1. That is, four multi-cavity boards 60 are arranged over the mold surface 8h of the lower mold 8 of the mold 6, and, thereafter, the mold 6 is clamped and resin sealing is performed. Here, the resin sealing can be performed by setting the depths of the air vents 7c to a fixed value irrespective of the thickness of the multi-cavity board 60.

Accordingly, with the use of ^{method of} the fabrication ~~method~~ of the semiconductor integrated circuit device of the embodiment 2, it is possible to obtain ~~the~~ ^{the} substantially same advantageous effects as the advantageous effects of the embodiment 1.

Further, with the use of the movable pins 1, which are arranged in respective air vents 7c, the resin sealing is

performed by setting the depths of respective air vents 7c to a fixed value irrespective of the thickness of the multi-cavity board 60. Accordingly, even when a plurality of boards are sealed with resin using one mold 6 at a time in the same manner as the embodiment 2, without being affected by the irregularities of the thickness among the boards, the irregularities are absorbed by the mold 6, whereby the constitution is very effective.

For example, if only one of four multi-cavity boards 60 is formed rather thick, conventionally, ^aleaking of resin occurs with respect to ^{the} other three molds when the resin sealing is performed at ^{one} a time. However, the resin sealing in assembling of the semiconductor integrated circuit device according to the embodiment 2 is not affected by the irregularities in the thickness among the boards, and hence, drawbacks such as ^{the} leaking of resin, insufficient resin filling and defective welding can be avoided in the same manner as the embodiment 1.

Accordingly, the fabrication cost in resin sealing can be reduced.

Other ^{methods of} fabrication ^{the} method of semiconductor integrated circuit device according to the embodiment 2 and ~~the~~ other effects [^] which can be obtained by the other fabrication methods [^] are substantially equal to those of the embodiment 1, and hence, ^a ~~the~~ repeated explanation ^{the} is omitted.

Although the invention made by inventors of the present

invention
application has been specifically explained in conjunction with the embodiments 1 and 2, the present invention is not limited to the above-mentioned embodiments 1 and 2, and various modifications can be made without departing from the gist of the present invention.

For example, although ~~the~~ cases in which the semiconductor integrated circuit device is constituted of the CSP 43, 50 and the card type package 59 ~~are~~ ^{have been} explained in ^{conjunction with} the above-mentioned embodiments 1 and 2, the above-mentioned semiconductor integrated circuit device may be constituted of ^{types of} other semiconductor integrated circuit device, such as a BGA (Ball Grid Array) type display device, a LGA (Land Grid Array) type display device or the like, provided that the semiconductor integrated circuit device is of the resin sealing type which can be assembled by performing ~~the~~ resin sealing using the board.

Further, although ^a ~~the~~ case in which the movable pins 1 formed on the upper mold 7 are mounted individually one by one corresponding to respective air vents 7c ^{has been considered} ^{in conjunction with} the embodiment 1, 2, the movable pins 1 may be ^{constituted by} a member such as a movable block piece formed as one body corresponding to a group of the air vents 7c.

Further, the board may be a metal plate, such as a lead frame, irrespective of the board over which the printed wiring is formed.

The advantageous effects which are obtained by the ~~typical~~ invention among the ~~inventions~~ ^{features} disclosed in the present application are briefly recapitulated as follows.

Since the resin sealing is performed with air vents having ~~the~~ ^{depths} set to a fixed value irrespective of the thickness of the board, insufficient resin filling, leaking of resin or imperfect welding within the cavity can be avoided, and the yield rate of the products can be enhanced.